

Nuances les plus couramment utilisées	Composition nominale					Dureté HV garanties	Dureté HRC garanties	Corrosion	Tenue à chaud	Abrasion	Ténacité
	Co	C	Cr	W	autres						
Spreadsheet of metal grades :	Nominal chemistry					Guaranteed vickers hardness chart	Guaranteed rockwell c hardness chart	Corrosion	Elevated temperature resistance	Abrasion	Toughness
	Co	C	Cr	W	others						
Alacrite XSH CoCr20NiW	Base	0,1	20	15	Ni:10	180	20	***	****	*	****
Alacrite 164N CoCr28Mo6	Base	0,2	28		Mo:6	250	22	****	***	*	**
Alacrite 163D CoCr28Mo6	Base	0,3	28		Mo:6	320	28	***	***	*	****
Alacrite 52N CoCr	Base	0,5	25,5	7,5	Ni:10	240	22	***	****	*	***
Alacrite 601 CoCr26W6	Base	0,5	26	6		360	30	***	****	***	***
Alacrite 502 CoCr31W14	Base	1	31	14		460	42	***	***	***	***
Alacrite 602 CoCr29W5	Base	1,1	29	5		380	36	***	**	**	***
Alacrite 553 CoCr30W	Base	1,5	30	8		470	42	***	***	***	***
Alacrite 483 CoCr31W18	Base	1,5	31	18		600	52	***	***	****	**
Alacrite 543 CoCr25W12	Base	1,6	25	12,5		520	46	***	***	****	**
Alacrite 554 CoCr30W8	Base	1,8	30	8		480	43	***	***	***	**
Alacrite 505 CoCr32W13	Base	2,5	32	13		575	51	***	**	****	*